

Fluids	Dynamic and static seal												Static seal only		Reccomended compounds	
	NBR (ME00XX/YY)	EPDM (ME01XX/YY)	FPM (ME02XX/YY)	SBR (ME04XX/YY)	CR (ME06XX/YY)	HNBR (ME08XX/YY)	AU (ME10XX/YY)	ACM (ME11XX/YY)	IIR (ME13XX/YY)	BR (ME14XX/YY)	CSM (ME16XX/YY)			MVQ (ME03XX/YY)		MFQ (ME5XX/YY)
Pothas	C	P	P	C	-	-	C	-	P	-	C			C	-	ME00XX/YY
Propane	C	N	C	-	-	C	-	-	-	-	-			N	-	ME00XX/YY
Epoxy resins	N	C	N	-	-	-	-	-	-	-	-			N	-	ME01XX/YY
Sodium silicate	C	C	C	C	-	-	-	-	C	-	C			C	-	ME01XX/YY
Aluminium sulphate	C	C	C	C	-	-	-	-	C	-	C			-	-	ME01XX/YY
Ammonium sulphate	C	C	-	C	-	-	-	-	C	-	C			C	-	ME00XX/YY
Iron sulphate	C	C	C	C	-	-	-	-	C	-	C			-	-	ME00XX/YY
Magnesium sulphate	C	C	C	C	-	-	-	-	C	-	C			C	-	ME00XX/YY
Nickel sulphate	C	C	C	C	-	-	-	-	C	-	C			-	-	ME00XX/YY
Potassium sulphate	C	C	C	C	-	-	C	-	C	-	C			C	-	ME00XX/YY
Copper sulphate	S	C	C	-	N	-	-	-	C	-	C			C	-	ME01XX/YY
Sodium sulphate	C	C	C	C	-	-	C	-	C	-	C			C	-	ME00XX/YY
Zinc sulphate	-	C	C	-	-	-	-	-	C	-	C			C	-	ME02XX/YY
Sodium sulphite	C	C	C	C	-	-	-	-	C	-	C			-	-	ME00XX/YY
Barium sulphide	C	C	-	C	-	-	-	-	C	-	C			C	-	ME00XX/YY
Soapy solution	C	-	C	C	S	-	C	-	C	-	C			C	-	ME10XX/YY
Solvents for paints	N	N	N	N	N	-	P	-	-	-	N			P	-	ME10XX/YY
Chlorine-based dry solvents	N	-	S	N	N	-	-	-	-	-	-			N	-	ME02XX/YY
Carbon tetrachloride	N	-	C	N	N	-	N	-	N	-	N			N	-	ME02XX/YY
Sodium thiosulphate	C	C	C	C	-	-	-	-	C	-	C			-	-	ME00XX/YY
Toluol	N	N	C	N	N	-	N	-	N	-	N			N	-	ME02XX/YY
Trichloroethylene	N	N	C	N	N	-	N	-	N	-	N			N	-	ME02XX/YY
Turpentine	C	-	C	N	N	-	N	-	N	-	N			N	-	ME02XX/YY
Steam at 100°	N	C	P	-	-	-	-	-	-	-	-			N	-	ME01XX/YY
Steam upto 200°	N	C	N	N	N	N	N	N	S	N	-			P	N	ME01XX/YY
Ammonia steam: cold	P	C	N	C	C	-	P	-	P	-	C			C	-	ME04XX/YY
warm	C	C	C	C	C	-	P	-	C	-	C			C	-	ME04XX/YY
Wine and whisky	C	C	-	C	C	-	-	-	C	-	C			-	-	ME00XX/YY
Xylene	N	N	C	N	N	N	N	-	-	-	N			N	-	ME02XX/YY
Sulphur	C	C	P	-	C	-	C	-	C	-	S			C	-	ME00XX/YY